



WATER & OIL REPELLENT NANOSTRUCTURED IMPREGNATION COMPOUND

Product Description	Nano PoreKote M is an innovative water and oil repellent with waterproofing properties. It is a water-based fluorinated nano emulsion that exhibits high penetration ability & hydrophobic performance, suitable for exterior and interior building surfaces. Nano shows resistance against UV and alkalis.
Fields of Application	 Nano PoreKote M is suitable for the impregnation of vertical, horizontal or inclined mineral porous substrates, such as: marbles granite limestones sandstones *All the surfaces have to be continuous without cracks.
Properties-Advantages	 High penetration and deep waterproofing, due to its nano-molecular structure, reducing the water uptake Early water repellence, reacting chemically and bonding with the substrate, thus providing durable hydrophobicity and oleophobicity It is resistant to alkalis and prevents from efflorecence Improves heat insulating properties on the substrate, reducing the heat conductivity Reduces dirt pick-up and limits fungal growth, thus facilitating the cleaning of the surface, allowing it at the same time to breathe Does not form sticky silicone films Does not change the original appearance of the surface Solvent-free, VOC-free and PFOA-free (does not contain toxic substances) Easy to apply

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of BASICHEM[®]. It is offered as a service to designers and contractors in order to help them find potential solutions. However, as manufacturer, BASICHEM[®] does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.



WATER & OIL REPELLENT NANOSTRUCTURED IMPREGNATION COMPOUND

Technical Characteristic

Appearance/Color Density (EN ISO 2811.01) Consumption

Drying time (250C, 65% RH) Recoating time (250C, 65% RH) Full cure time (250C, 65% RH) Water penetration value (RILEM Test Method 11.4) Liquid water permeability (EN 1062-3) Milky yellowish liquid 1.00 ± 0.01 kg/l 100-200ml/m² (The consumption depends on the application method and the absorptivity of the substrate) 1 hour < 2 hours 24 hours 0.00 ml/min (concrete surface) 0.0001 Kg/m²h^{0.5}

Application Condition

Relative atmospheric humidity	< 80%
Surface humidity content	< 4%
Application temperature	+5°C - +35°C

Porous surfaces: 200ml/m² Semi-polished surfaces: 60ml/m²

(The consumption depends on the application method and the absorptivity of the substrate)

Instructions for use

Consumption:

Surface preparation: Clean the surface from dust, mildew, dirt or any poorly adhering material. Use mechanical means or water blasting to clean the substrate. Avoid the use of detergents or soap, as they affect the adhesion of the product to the surface.

Application: Nano PoreKote M is ready for use. Apply one layer on a dry surface with a brush, roller, or spray gun, working from the lower to the higher part of the substrate on vertical surface. In absorptive surfaces apply a second layer at less than 2 hours after the first layer.

When the temperature is higher than +35°C / mist water (30g tap water/sqm) on the surface and after 5 minutes apply the PoreKote M .

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of BASICHEM[®]. It is offered as a service to designers and contractors in order to help them find potential solutions. However, as manufacturer, BASICHEM[®] does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.



WATER & OIL REPELLENT NANOSTRUCTURED IMPREGNATION COMPOUND

Special Notes It will reach its full repellence to water and oil within a few hours after its application and when the surface has been saturated during the application. For very absorptive and porous surfaces apply a second coat.

Nano PoreKote M should not be applied under wet conditions, or if wet conditions are expected to prevail during the drying period. If the surface has been cleaned by water blasting, it is advisable to let it dry for 2 - 3 days and apply the product afterwards.

In case of application on concrete than Allow 28 days for the curing time to pass between the casting new concrete and the product's application. Nano PoreKote M is not resistant to acids. For very absorptive and porous surfaces apply two coats.

Packaging	5 LITRES - 20 LITRES - 200 LITRES
Cleaning of Tools	Use tap water
Storage Stability	Nano PoreKote M is stable for 24 months when kept unopened in its original container, protected from frost and direct sunlight.





Tel: (+973) 1782 2069 • Fax: (+973) 1782 2269 • www.basichem-me.com

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of BASICHEM[®]. It is offered as a service to designers and contractors in order to help them find potential solutions. However, as manufacturer, BASICHEM[®] does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.